

# (12) UK Patent Application (19) GB (11) 2 270 172 (13) A

(43) Date of A Publication 02.03.1994

(21) Application No 9317829.1

(22) Date of Filing 27.08.1993

(30) Priority Data

(31) 4228790 (32) 29.08.1992 (33) DE

(71) Applicant(s)

E I Du Pont de Nemours and Company

(Incorporated in USA - Delaware)

1007 Market Street, Wilmington, Delaware 19898,  
United States of America

(72) Inventor(s)

Klaus Uwe Schonfelder

Karl-Heinz Wiedenmann

Uwe Michael Zakrzewski

(74) Agent and/or Address for Service

J A Kemp & Co

14 South Square, Gray's Inn, LONDON, WC1R 5LX,  
United Kingdom

(51) INT CL<sup>5</sup>

G03F 7/075

(52) UK CL (Edition M )

G2C CRPC C1B1F C1B1M C1E1G C1G2

(56) Documents Cited

EP 0448285 A

EP 0360618 A

EP 0225454 A

US 4786577 A

US 4693960 A

US 4689289 A

(58) Field of Search

UK CL (Edition L ) G2C CD15B9 CRA CRM CRPC CRPY

INT CL<sup>5</sup> G03F

(54) Tenable, radiation sensitive composition and its use in making colour proofs

(57) A tonable, radiation sensitive composition, whose adhesion properties can be controlled by the addition of a polydiorganosiloxane with polar and/or ethylenic unsaturated groups. Such a composition is applied to a support and a cover sheet is placed over the composition, the sheet being more readily removable due to the polysiloxane. Colour proofs may be made by removing the cover sheet, laminating the composition to a receptor, imagewise exposing, removing the support, toner developing the unexposed areas with the appropriate colour and repeating the operations using different originals and different coloured toners.

GB 2 270 172 A

GP-1095

TITLE

TONABLE, RADIATION SENSITIVE COMPOSITION AND  
PROCESS FOR THE GENERATION OF MULTICOLORED  
IMAGES USING SUCH A COMPOSITION

5

FIELD OF THE INVENTION

This invention relates to a tonable, radiation  
sensitive composition and in particular, to a process  
for making multicolored images using a composition that  
contains as a significant component (a) a compound that  
causes a change in the tackiness of the composition  
through exposure to actinic radiation and (b) a  
compound that influences the adhesion properties of the  
composition.

15

BACKGROUND OF THE INVENTION

Scanned color separations are used as artwork in  
the reproduction technique to produce offset- or relief  
printing plates. The color separations are proofed,  
before the exposure of the printing plates, using a  
color proofing process to determine if the later  
printing result represents an accurate tonal  
reproduction of the original.

20

Radiation sensitive recording materials which  
utilize differences in the tackiness of exposed and  
unexposed areas are used to form images in color  
proofing processes. A reproduction process is  
described for example, in Berg, German Patent 1210321  
(U.S. Patent 3,060,024); Chu, German Patent 1904058  
(U.S. Patent 3,620,726); Boyd, German Patent 1904059  
(U.S. Patent 3,582,327); Chu, German Patent 2004214  
(U.S. Patent 3,649,268); Buzzell, U.S. Patent  
4,356,253; and Bauer, European Patent 0243933 (U.S.  
Patent 4,892,802), in which a tacky, photopolymerizable  
recording material, consisting of a support and a

30

35

polymerizable layer that contains at least one addition- polymerizable monomer and a photopolymerization initiator, is hardened upon imagewise exposure. The exposed areas lose their tackiness in this case. The latent image is made visible by applying suitable toning materials, which adhere only to the unexposed, tacky areas. Excess toner can be removed from the exposed, non-tacky areas after the application. With this process, one obtains positive toned images of the artwork that look like pictures that were produced using printing inks.

Negative images of the artwork are obtained using light sensitive materials such as those described in Abele, U.S. Patent 4,243,741; Abele, U.S. Patent 4,346,162; and Grossa, U.S. Patent 4,604,340. These recording materials contain as light sensitive components either a dihydropyridine compound or a system from a dihydropyridine compound and a hexaarylbiimidazol compound.

Application of toner materials that consist mainly of fine particle powders can be carried out by dusting the imagewise exposed surface as described, for example, in Manger, U.S. Patent 4,215,193, and Gray, U.S. Patent 3,909,282. In another embodiment, the toner can be loosely attached to a special carrier and then transferred to the imagewise exposed surface by contacting it with this carrier. Such pigmented carrier layers are described in Frohlich, U.S. Patent 4,806,451, and Metzger, Canadian Patent 2,032,051.

The radiation sensitive recording materials consist usually of a support, a radiation sensitive layer and a coversheet. This coversheet is removed and the material is laminated to a receptor before the imagewise exposure takes place. The support can be removed before or after the exposure, depending on the material.

A recurring problem with this process is the inability to separate the coversheet cleanly from the radiation sensitive layer before lamination to the receptor, because the adhesion of the radiation sensitive layer to the coversheet is too high. Either the radiation sensitive layer separates partially from the support or some areas of the layer are pulled off by the coversheet. Naturally, such damaged layers can not be used for the color proofing process.

10       The adhesion balance between the radiation sensitive layer and the support can be improved somewhat by the addition of aliphatic polyesters with molecular weights between 1500 and 40000, such as described in Bauer, U.S. Patent 4,326,010. However the  
15       difficulties described above can still occur.

      Special polyorganosiloxane compounds are used because of their adhesion properties in release layers such as those for the supports of tacky labels. These are described in Weitemeyer, U.S. Patent 4,678,846;  
20       Weitemeyer, European Patent 284,863; and Weitemeyer, U.S. Patent 4,963,438. Such release layers, however, can not be compared with the tonable, radiation sensitive layers used in the described color proofing process, because they have to be removable from both  
25       the coversheet and the support, while still demonstrating good adhesion to the receptor as well as to the other recording layers.

      Polydimethylsiloxane is known from Nakamura, German Patent 3,337,303, as a material used to prevent  
30       the sticking of a photomask to photoresist materials. It is however unsuitable for use in the named tonable recording materials, since layers that contain polydimethylsiloxane, do not adhere sufficiently to the other recording layers.

35       Special silanes are suitable as additives for photoresist films, having a reduced residual layer

after development as described in Lauke, European Patent 329,009. This does not suggest, however, that silanes can be used for recording materials for color proofing processes, which have to have very specific  
5 adhesion balances.

Accordingly, one purpose of this invention is to eliminate the above-described problems in the color proofing process by optimizing the adhesion balance of a tonable, radiation sensitive recording layer to a  
10 coversheet and a support, in a way that allows selective removal of the coversheet first but the support is also removable. This must be achieved without damaging the recording layer during either removal process and without influencing the adhesion of  
15 the recording layer to the receptor or to other recording layers. In addition, a defect free toner application to the imagewise exposed layer must be assured.

#### 20 SUMMARY OF THE INVENTION

This invention describes a tonable, radiation sensitive composition comprising:

- 25 (a) at least one compound, that after exposure with actinic radiation, causes a change in the tackiness of the composition;
- (b) a photoinitiator or a photoinitiator system;
- (c) a compound selected to influence the adhesion properties of the composition; and
- (d) optionally a polymeric binder or a binder  
30 composition;

wherein at least one polydiorganosiloxane with polar and/or ethylenic unsaturated groups is used at least partially to control the adhesion.

In another embodiment, a process for forming  
35 colored images using this composition is described.

### DETAILED DESCRIPTION OF THE INVENTION

Suitable additives to control the adhesion properties of tonable, radiation sensitive recording layers are according to the invention

5 polydiorganosiloxanes with polar and/or unsaturated groups. Alkyl, substituted alkyl, aryl and substituted aryl groups are suitable organo groups. Especially suitable are alkyl groups with 1 to 5 carbon atoms and phenyl groups. Acryl and/or methacryl groups can be

10 used as ethylenic unsaturated groups. Suitable polar groups are amino, hydroxy, carboxy, alkoxy, halo, epoxy and carboxylic acid esters. Hydroxy, carboxy and alkoxy groups are especially preferred.

The polysiloxanes should have a minimum of 10

15 siloxane units, preferably 20 to 60 of such units, especially recommended 25 to 40. ~~alpha~~, ~~omega~~-Hydroxy functional polydimethylsiloxane-polycaprolactone copolymers have shown themselves as especially suitable. The number of caprolactone units should be

20 at least 3, preferably 5 to 40, and more preferably 7 to 30. The molecular weight of the polydiorganosiloxane is preferably equal to or greater than 2,000, especially 3,000 to 15,000.

The named polysiloxanes can be used as the only

25 adhesion additive or in combination with other such additives. Suitable for mixtures are for example the polyesters described in Bauer, U.S. Patent 4,326,010, especially polycaprolactones.

The tonable, radiation sensitive mixtures

30 according to the invention should contain 0.05 to 0.7% by weight of polydiorganosiloxanes with polar and/or unsaturated groups. When used in mixtures with other adhesion additives, 0.05 to 0.2% by weight of the polysiloxanes of this invention are preferred.

35 Especially preferred, however, is the use of these polysiloxanes as the only additives for controlling the

adhesion properties of the composition. In this case, 0.3 to 0.7 weight % is preferred.

Positive tonable, photohardenable compositions such as those described, for example, in Berg, German Patent 1210321 (U.S. Patent 3,060,024); Chu, German Patent 1904058 (U.S. Patent 3,620,726); or Chu, German Patent 2004214 (U.S. Patent 3,649,268), as well as negatively tonable, systems that become tacky after exposure, as described, for example, in Abele, U.S. Patent 4,243,741; Abele, U.S. Patent 4,346,162; and Grossa, U.S. Patent 4,604,340, can be used in the radiation sensitive compositions of this invention. The named negatively tonable recording materials contain either a dihydropyridine compound or a light sensitive composition formed from a hexaarylbisimidazole compound and a dihydropyridine.

Positive tonable photopolymerizable recording materials are preferentially used for this invention. The materials described in Bauer, U.S. Patent 4,734,356, and Bauer, European Patent 0243933 (U.S. Patent 4,892,802), are especially preferred. These materials contain a polymeric binder, at least one photopolymerizable compound, a photoinitiator and, optionally, other additives such as plasticizers, sensitizers, fillers, antioxidants and brighteners. The preferred binders, described in Bauer, European Patent 0243933 (U.S. Patent 4,892,802), either have a glass transition temperature equal to or lower than 70°C, or, if they contain metal ions, have a glass transition temperature equal to or lower than 80°C. The latter are crosslinked by the addition of metal ions. Thermoplastic binders based on polyacrylate and/or polymethacrylate that have the salt forming groups in the form of either acrylic acid or methacrylic acid have proven especially useful. The metal ions are preferably magnesium, calcium,

strontium, barium, aluminum, tin, zinc, cadmium, titanium, zirconium and manganese. They are added as salts, preferably as chelates.

5 The amount of binder, or mixture of binders is generally 20 to 90 weight %, preferably 30 to 70 weight %, relative to the total weight of the dry recording layer. The amount of salt forming groups is 2 to 20 weight %, preferably 2 to 15 weight %, whereby at least 10 weight % of these groups should be crosslinked  
10 through the metal ions.

The known monomers and oligomers are suitable as photopolymerizable compounds. Preferably used are compounds with several addition polymerizable, ethylenic unsaturated groups. Combinations of these  
15 compounds are also possible. Especially suitable are acrylic- and methacrylic acid from multivalent acyclic and cyclic polyols as well as aromatic hydroxy compounds, such as ethylene glycol diacrylate; diethylene glycol diacrylate; glycerin di- and  
20 triacrylate; 1,3-propanediol dimethacrylate; trimethylolpropane trimethacrylate; hexamethyleneglycol diacrylate and the bisacrylates; and the bismethacrylates of bisphenol-A alkoxylated with epichlorohydrin, as described in Bauer, U.S. Patent  
25 4,734,356. The monomers are usually used in amounts of 10 to 80 weight %, preferably 20 to 60 weight %.

Practically all compounds known as photoinitiators can be used in amounts from 0.01-15 weight percent. Examples of suitable photoinitiators and photo-  
30 initiators systems are: dibenzoyl, dibenzoyldimethylketal, benzoin, benzoinisopropylether, alpha-methylbenzoin, 1,4-naphthoquinone, Michler's ketone and benzophenone as well as systems of substituted thioxanthenes and tertiary amines.

35 In addition, 5 to 30 weight percent of one or several plasticizers may be used, for example: alkyl



phosphates; polyethyleneglycols: polyethylene oxides; and diesters of phthalic acid, adipic acid and caproic acid. Liquid acrylate and/or methacrylate polymers or butadiene/acrylonitrile co-polymers with salt forming groups are preferred.

Using known methods, the tonable, radiation sensitive compositions, can be coated on suitable, preferably transparent, supports and then dried. Suitable supports are, for example, plastic films from polyethylene, polypropylene, polyamide and polyester. Polyethylene terephthalate film is the preferred support. If non-transparent supports are used, they will be removed before the imagewise exposure.

The side of the recording layer opposite the support is covered with a flexible coversheet, such as a thin film of polystyrene, polyethylene, polypropylene or poly-ethylene terephthalate. Polypropylene film is preferred.

The thickness of the recording layer can be between 2 microns and 1 millimeter depending on the desired application.

The radiation sensitive materials have their maximum sensitivity in the ultraviolet region, preferably in the wavelength between 250 and 450 nm. All radiation sources that supply an effective amount of this radiation are therefore suitable for the exposure. For example, xenon lamps, mercury vapor lamps and carbon arc lamps, lasers, fluorescent lamps with ultraviolet emitting phosphors, and electronic flashes are all suitable.

The toning of the imagewise exposed recording layer can be accomplished by dusting with toner materials that consist mainly of finely divided powders, such as those described in Manger, U.S. Patent 4,215,193, and Gray, U.S. Patent 3,909,282. It can also be done with pigmented toning foils, that contain

the toning material loosely bound on a separate carrier. Such toning foils are described in, for example, Metzger, Canadian Patent 2,032,051; Frohlich, U.S. Patent 4,806,451; and Delaney, U.S. Patent  
5 4,902,363.

#### INDUSTRIAL APPLICABILITY

The composition of this invention can, for example, be used advantageously for the reproduction of  
10 line and screen images in graphic arts and other industrial applications. One primary application however, lies in the production of single- and multi-colored images and in color proofing processes.

The procedure for using the radiation sensitive  
15 composition of the invention in a color proofing process consists of the following process steps. After the removal of the coversheet, a positively tonable photopolymerizable recording material is laminated to a receptor, whereby the photopolymerizable layer has a  
20 higher adhesion to the surface of the receptor than to the support, both in the polymerized and the unpolymerized state.

Paper, cardboard, metals, films or plates made from polymers such as polyethylene, polyester,  
25 polyvinyl chlorides, polyamides are suitable receptors. The receptor can be unchanged or have a coating that contains, in addition to the normal components, other substances such as pigments, fillers, optical brighteners, ultraviolet absorbers, and antistatic  
30 agents. Then the material is exposed by actinic radiation through the transparent support and art work, e.g., a scanned color separation positive of a first color yielding non-tacky areas in the exposed areas. The support is then removed by delaminating.  
35 The latent image formed on the receptor is made visible by applying a toner that adheres to the unexposed areas

of the layer. The toner is removed from the hardened areas, leaving them totally free of toner.

A second layer of the photopolymerizable material is then laminated to the picture after removal of the coversheet. It is exposed and toned under the same conditions using a scanned color separation positive of a second color as art work. This step is then repeated with the color separation for a third color and if desired for a scanned black separation positive. Hence, a four color picture corresponding to the color separations is obtained.

Subsequently, a protective layer can be applied to the single or multi-colored picture. This protective layer can consist of an additional laminate of the photohardenable material, from which after an overall exposure, the support is removed.

If a negatively tonable recording material, one that becomes tacky after exposure, is used, the process is the same except that a scanned color separation negative is used instead of the scanned color separation positive.

With the tonable, radiation sensitive compositions of this invention, or the recording materials made from them, the color proofing processes described can be performed significantly simpler and with fewer problems, since when the coversheet is removed from the recording layer defects do not form in the layer nor does the support delaminate. In addition, the recording layers adhere well to each other and to the receptor and a defect free toning quality is guaranteed.

The following examples illustrate the invention. The ingredients are listed by weight unless otherwise noted.

35

EXAMPLESEXAMPLE 1 (Comparison example)

5 A photopolymerizable recording material of the type disclosed in Bauer, European Patent 0243933 (U.S. Patent 4,892,802) was generated according to Example 7 of the Bauer patent.

The 15% solution in dichloromethane contained:  
diacrylate ester of a bisphenol-A-epoxy resin, formed  
10 from bisphenol-A and epichlorohydrin, 18.48 g  
(viscosity at 25°C 1,000,000 cps); trimethylolpropane  
trimethacrylate, 13.66 g; 7-(4'-chloro-6'-diethylamino-  
1',3',5',-triazin- 4'-yl)-amino-3-phenyl-coumarin, 2.06  
g; 2-mercaptobenzoxazole, 0.83 g; 2,2'-bis  
15 (o-chlorophenyl)- 4,4',5,5',-tetraphenylbisimidazol,  
1.71 g; trimethylolpropane, 5.08 g; glycerol  
triacetate, 6.75 g; methoxyhydroquinone, 0.022g;  
1,4,4-trimethyl-2,3-diazobicyclo-(3,2,2,)-non-2-en-2,3-  
dioxide, 0.05 g; diethylhydroxylamine, 0.09 g;  
20 ethylacrylate/-methyl methacrylate/acrylic acid  
copolymer (57/39/4), molecular weight (MW): 192,000,  
18.06 g; ethylacrylate/acrylate copolymer MW: 7,000,  
Tg: -14°C, 5.40 g; ethylacrylate/methyl  
methacrylate/acrylic acid copolymer (17/71/12), MW:  
25 200,000, 25.15 g; zinc acetyl acetonate, (2.45 g)  
dissolved in 37.0 g methanol, 39.45 g;  
polycaprolactone, MW: 15 000, 0.20 g.

This coating solution was coated on a polyethylene  
terephthalate film (12.5 microns), so that after drying  
30 a 4 micron thick polymerizable layer was obtained.  
Then a 19 micron thick polypropylene coversheet was  
laminated to this layer. The force required to remove  
the coversheet from the photopolymerizable recording  
layer was measured as described in Bauer, U.S. Patent  
35 4,326,010, using an Instron® Model 4301 Universal  
Tester. The coversheet was removed at an angle of

about 180° to the edge of the recording layer. The removal force for this material was 4.5 N/200 mm.

#### EXAMPLE 2

5 Two photopolymerizable recording materials were produced as described in Example 1, however they contained in addition 0.1% for the first material and 0.3% for the second material of a alpha, omega-hydroxyfunctional polydimethylsiloxane -  
10 polycaprolactone copolymer with about 30 siloxane units, about 27 caprolactone units and a molecular weight of about 8,550. The coversheets could be removed more easily from the recording layers and without defects. The removal forces were 3.0 N/200 mm  
15 (for 0.1% copolymer) and 1.7N/200 mm (for 0.3% copolymer). The adhesion to the support was not negatively influenced.

#### EXAMPLE 3

20 Two photopolymerizable recording materials were produced as described in Example 1, however they contained in addition 0.05% in the first material and 0.3% in the second material of a acrylate functional polydimethylsiloxane with a viscosity of about 1400  
25 mPa. s. The coversheet could be removed more easily and without defects from both recording layers. The removal forces were 2.6 N/200 mm (0.05%) and 0.7 N/200 mm (0.3%), respectively. The adhesion to the support was not negatively influenced.

30

#### EXAMPLE 4

A photopolymerizable recording material was produced analogous to Example 1, except that the polycaprolactone was replaced by 0.5% of the  
35 polysiloxane described in Example 2. The adhesion to the coversheet (1.3 N/200 mm) was significantly reduced

in comparison to material without any adhesion additive  
(5.6 N/200 mm). The coversheet could be more easily  
removed when compared to the material in Example 1 and  
the adhesion to the support was not negatively  
5 influenced.

#### EXAMPLE 5

As described in Example 4, a photopolymerizable  
recording material was produced, that contained as  
10 additive only a polysiloxane; 0.5% of a alpha,omega-  
hydroxyfunctional polydimethylsiloxane -  
polycaprolactone copolymer with about 30 siloxane  
units, about 9 caprolactone units and a molecular  
weight of about 4,550. With this material the  
15 coversheet could also be easily removed without  
negatively affecting the adhesion to the support.  
(The removal force was 0.8 N/200 mm.)

#### EXAMPLE 6

20 Four photopolymerizable recording materials  
according to Example 2 and pigmented transfer layers of  
the colors cyan, magenta, yellow, and black according  
to Example 12 in the Metzger, Canadian Patent  
2,032,051, were prepared for the formation of a four  
25 color proof. After the coversheet was removed, the  
first photopolymerizable recording material was  
laminated to a receptor. It was then exposed through a  
scanned cyan color separation positive in a vacuum  
frame using a metal halide lamp (3000 watt) and an  
30 ultraviolet filter at a distance of 95 cm for 42 sec.  
After the support was removed, the cyan transfer layer  
was laminated to the imagewise exposed layer and  
immediately peeled off. The pigment from the transfer  
layer adhered only to the unexposed, tacky areas, and a  
35 positive cyan image of the art work was obtained.

A second layer of the positively tonable photopolymerizable recording material was laminated to the cyan image and exposed through the corresponding magenta color separation as described above. After the support was removed, the magenta transfer layer was laminated to the imagewise exposed layer and peeled off. The pigment from the transfer layer adhered only to the unexposed, tacky areas, and a positive magenta image was obtained. The process steps were repeated for the colors yellow and black. Then a protective layer is applied in the normal way. A four color proof of excellent brightness and sharpness with a resolution from 1% to 99% dots on a 60 line/cm screen, which represents an exact replication of the original, was obtained. The coversheets of the recording materials could be removed easily and without defects. The adhesion of the recording layers to each other and to the receptor was excellent.

Having described the invention, we now claim the following and their equivalents.

25

30

35

CLAIMS

1. A tonable, radiation sensitive composition comprising:
  - a) at least one compound, which after exposure to  
5 actinic radiation causes a change in the tackiness of the composition;
  - b) a photoinitiator or a photoinitiator system;
  - c) a compound selected to influence the adhesion properties of the composition; and
  - 10 d) optionally a polymeric binder or binder mixture,  
wherein at least one polydiorganosiloxane with polar and/or ethylenic unsaturated groups is used at least partially to control adhesion.
- 15 2. A composition according to claim 1 wherein said radiation sensitive composition is a positive working tonable composition.
3. A composition according to claim 1 or 2, wherein said compound influencing the adhesion balance is a  
20 polydiorganosiloxane with polar and/or ethylenic unsaturated groups and the organo groups of said polydiorganosiloxane consist of alkyl groups with 1 to 5 carbon atoms and/or phenyl groups.
4. A composition according to claim 3, wherein said  
25 polydiorganosiloxane contains a polar group selected from hydroxy, alkoxy, and carboxy.
5. A composition according to claim 4, wherein said



polydiorganosiloxane contains at least 10 siloxane units.

6. A composition according to claim 1 or 2, wherein said compound influencing the adhesion balance is a polydiorganosiloxane/polyester copolymer.

5 7. A composition according to claim 6, wherein said polydiorganosiloxane/polyester copolymer contains at least 10 siloxane units.

8. A composition according to claim 3, wherein said radiation sensitive composition contains from 0.05% to 0.7%  
10 by weight of the polydiorganosiloxane component for influencing the adhesion balance.

9. A tonable, radiation sensitive recording material comprising:

- a) a support;
- 15 b) a tonable, radiation sensitive layer; and
- c) a coversheet;

wherein said tonable, radiation sensitive layer comprises a polydiorganosiloxane compound as defined in claim 3.

10. A process for the formation of images comprising:

20 a) laminating to a receptor after removing the coversheet the tonable, radiation sensitive recording material as claimed in claim 9;

b) imagewise exposing through the support the tonable, radiation sensitive layer;

25 c) peeling off the support; and

d) applying a toning material to the tacky areas of the exposed layer.

11. A process for the formation of a multicolored image comprising:

- a) laminating to a receptor after removing the coversheet the tonable, radiation sensitive recording material as defined in claim 9;
- b) imagewise exposing through the support the tonable, radiation sensitive layer;
- c) peeling off the support;
- d) applying a toning material to the tacky areas of the exposed layer; and
- e) repeating steps a) to d) one or more times, whereby in step a) a new layer of tonable, radiation sensitive recording material is laminated to the previously formed radiation sensitive layer, which has been processed according to steps a) to d) to produce a one-color image.

12. A process according to claim 10 or 11, wherein the support is removed prior to imagewise exposure.

**Patents Act 1977**  
**Examiner's report to the Comptroller under**  
**Section 17 (The Search Report)**

Application number

GB 9317829.1

**Relevant Technical fields**

(i) UK Cl (Edition L ) G2C (CRA, CRPC, CRPY, CRM,  
 CD15B9)

(ii) Int Cl (Edition 5 ) G03F

**Search Examiner**

M K B REYNOLDS

**Databases (see over)**

(i) UK Patent Office

(ii)

**Date of Search**

7 OCTOBER 1993

Documents considered relevant following a search in respect of claims 1-12

Category (see over)	Identity of document and relevant passages	Relevant to claim(s)
X	EP 0448285 A (OKI) Pages 3-6, Ex's	1 and 3 at least
X	EP 0360618 A (FUJI) Pages 2-10, Ex's	1 at least
X	EP 0225454 A (IBM) Pages 2-3, Ex's	1, 6 and 7 at least
X	US 4786577 (FUJI) Columns 4-16, Ex's	1 and 4 at least
X	US 4693960 (IBM) Column 3 and Ex	1 at least
X	US 4689289 (GEC) Column 8 and Ex's	1 at least

SF2(p)

swA - doc99\fil001753

Category	Identity of document and relevant passages	Relevant to claim(s)

### Categories of documents

**X:** Document indicating lack of novelty or of inventive step.

**Y:** Document indicating lack of inventive step if combined with one or more other documents of the same category.

**A:** Document indicating technological background and/or state of the art.

**P:** Document published on or after the declared priority date but before the filing date of the present application.

**E:** Patent document published on or after, but with priority date earlier than, the filing date of the present application.

**&:** Member of the same patent family, corresponding document.

**Databases:** The UK Patent Office database comprises classified collections of GB, EP, WO and US patent specifications as outlined periodically in the Official Journal (Patents). The on-line databases considered for search are also listed periodically in the Official Journal (Patents).